

Technical product information

Direct thermal film, white, matte, coated, permanently adhesive

Materialcode: MR-FD

Status: Okt-26

Upper

White direct thermal film with one-sided protective coating

Feature	Value	Unit	Standard
Basis weight	approx. 52	g/m ²	ISO 536
Thickness	approx. 66	µm	ISO 534
Tensile strength (MD)	approx. 80	N/15 mm	ISO 527
Tensile strength (CD)	approx. 160	N/15 mm	ISO 527
Opacity	approx. 87	%	ISO 2471
Reaction color	Black		

Adhesive

Permanent acrylate-based pressure-sensitive adhesive

Feature	Value
Initial adhesive strength	strong
Final adhesive strength	strong
Shear strength	very strong

Liner

White, supercalendered glassine paper

Feature	Value	Unit	Standard
Basis weight	approx. 54	g/m ²	ISO 536
Thickness	approx. 47	µm	ISO 534

Adhesive bond

Feature	Value	Unit	Standard
Basis weight	approx. 117	g/m ²	ISO 536
Thickness	approx. 123	µm	ISO 534
Minimum bonding temperature	-10	°C	
Application temperature	-30 to 50	°C	

The information provided describes the product in its essential technical characteristics. It is for general guidance purposes and does not constitute a guarantee or assurance of specific properties. The suitability of the material for the respective purpose is to be checked by the user on his own responsibility. Labelident assumes no liability beyond the obligations regulated by law or specified in the general terms and conditions of sale. Technical changes in the context of product development are reserved. Labelident is not the manufacturer of the raw material described.

Technical product information

Direct thermal film, white, matte, coated, permanently adhesive

Materialcode: MR-FD

Status: Okt-26

Shelf life

The material should be stored at a temperature of 20 ± 5 °C and a relative humidity of $45 \pm 5\%$ dry, protected from light and in the original packaging. Moisture, heat and direct sunlight should be avoided. If stored properly, the shelf life is 1 year from the date of manufacture.

Conformities

It must only be in direct contact with food that experience has shown to be washed or peeled before consumption. The pressure-sensitive adhesive used may be in direct contact with dry, moist and greasy foods to which a correction factor of at least 2 can be assigned. The pressure-sensitive adhesive used was developed for the removal of label material in the recycling process of PET and HDPE packaging.

The information provided describes the product in its essential technical characteristics. It is for general guidance purposes and does not constitute a guarantee or assurance of specific properties. The suitability of the material for the respective purpose is to be checked by the user on his own responsibility. Labelident assumes no liability beyond the obligations regulated by law or specified in the general terms and conditions of sale. Technical changes in the context of product development are reserved. Labelident is not the manufacturer of the raw material described.