

# Technical product information

Polyester, transparent, matte, coated, permanently adhesive

Material code: MB-CR

Status: Feb-26

## Upper

Transparent, matt polyester film

Feature	Value	Unit	Standard
Basis weight	approx. 75	g/m <sup>2</sup>	ISO 536
Thickness	approx. 60	µm	ISO 534
Elongation (MD)	approx. 165	%	ISO 527
Elongation (CD)	approx. 210	%	ISO 527
Transparency	approx. 90	%	DIN 53147

## Adhesive

Permanent acrylate-based pressure-sensitive adhesive

Feature	Value
Initial adhesive strength	strong
Final adhesive strength	very strong
Shear strength	strong

## Liner

White Kraft Paper Coated on One Side

Feature	Value	Unit	Standard
Basis weight	approx. 120	g/m <sup>2</sup>	ISO 536
Thickness	approx. 116	µm	ISO 534

## Adhesive bond

Feature	Value	Unit	Standard
Basis weight	approx. 218	g/m <sup>2</sup>	ISO 536
Thickness	approx. 198	µm	ISO 534
Minimum bonding temperature	0	°C	
Application temperature short-term up to 200 °C - Hot fixation	-30 to 150	°C	

The information available describes the product in its essential technical characteristics. They are for general guidance and do not constitute a guarantee or assurance of specific characteristics. The suitability of the material for the respective application must be checked by the user on his own responsibility. Labelident does not accept any liability beyond the obligations regulated by law or specified in the general terms and conditions of sale. Technical changes in the context of product development are reserved. Labelident is not the manufacturer of the raw material described.

# Technical product information

Polyester, transparent, matte, coated, permanently adhesive

Material code: MB-CR

Status: Feb-26

## Shelf life

The material should be stored at a temperature of  $20 \pm 5$  °C and a relative humidity of  $45 \pm 5\%$  dry, protected from light and in the original packaging. Moisture, heat and direct sunlight should be avoided. When stored properly, the shelf life is 4 years from the date of manufacture.

The information available describes the product in its essential technical characteristics. They are for general guidance and do not constitute a guarantee or assurance of specific characteristics. The suitability of the material for the respective application must be checked by the user on his own responsibility. Labelident does not accept any liability beyond the obligations regulated by law or specified in the general terms and conditions of sale. Technical changes in the context of product development are reserved. Labelident is not the manufacturer of the raw material described.