

Technical product information

Paper, fluorescent red, matte, coated, permanently adhesive

Materialcode: MR/MB-LR

Status: Okt-26

Upper

Bright red, single-sided, fluorescent, wood-free paper, certified according to FSC® Mix Credit

Feature	Value	Unit	Standard
Basis weight	approx. 80	g/m ²	ISO 536
Thickness	approx. 93	µm	ISO 534

Adhesive

Permanent acrylate-based pressure-sensitive adhesive

Feature	Value
Initial adhesive strength	very strong
Final adhesive strength	strong

Liner

Brown satin glassine paper

Feature	Value	Unit	Standard
Basis weight	approx. 54	g/m ²	ISO 536
Thickness	approx. 47	µm	ISO 534

Adhesive bond

Feature	Value	Unit	Standard
Thickness	approx. 154	µm	ISO 534
Minimum bonding temperature	0	°C	
Application temperature	-20 to 80	°C	

Shelf life

The material should be stored at a temperature of 20 - 25 °C and a relative humidity of 40 - 50 % dry, protected from light and in the original packaging. Moisture, heat and direct sunlight should be avoided. If stored properly, the shelf life is 2 years from the date of manufacture.

The information provided describes the product in its essential technical characteristics. It is for general guidance purposes and does not constitute a guarantee or assurance of specific properties. The suitability of the material for the respective purpose is to be checked by the user on his own responsibility. Labelident assumes no liability beyond the obligations regulated by law or specified in the general terms and conditions of sale. Technical changes in the context of product development are reserved. Labelident is not the manufacturer of the raw material described.

Technical product information

Paper, fluorescent red, matte, coated, permanently adhesive

Materialcode: MR/MB-LR

Status: Okt-26



Conformities

The outer material is made of paper that is certified according to FSC® Mix Credit, which is suitable for applications in the food industry. According to the manufacturer, the adhesive can be used for direct contact with dry, moist and greasy foods with a reduction factor of at least 3.

The information provided describes the product in its essential technical characteristics. It is for general guidance purposes and does not constitute a guarantee or assurance of specific properties. The suitability of the material for the respective purpose is to be checked by the user on his own responsibility. Labelident assumes no liability beyond the obligations regulated by law or specified in the general terms and conditions of sale. Technical changes in the context of product development are reserved. Labelident is not the manufacturer of the raw material described.